

Data sheet

28.12.2019

Filter paper

Parameter*	Value*
Grade	MN 85/220
Basis weight	220 g/m ²
Thickness	1 mm
Filtration speed	15 s
Surface	smooth / glatt
Average retention capacity	0.4 µm
Maximum temperature	500 °C
Application	Glass fiber filter with organic binder, thick

*These data are typical values and must not be regarded as specification.



Data sheet

*These data are typical values and must not be regarded as specification.

www.mn-net.com



MACHEREY-NAGEL GmbH & Co. KG · Neumann-Neander-Str. 6-8 · 52355 Düren · Germany

DE/international:

Tel.: +49 24 21 969-0

Fax: +49 24 21 969-199

E-mail: info@mn-net.com

CH:

Tel.: +41 62 388 55 00

Fax: +41 62 388 55 05

E-mail: sales-ch@mn-net.com

FR:

Tel.: +33 388 68 22 68

Fax: +33 388 51 76 88

E-mail: sales-fr@mn-net.com

US:

Tel.: +1 484 821 0984

Fax: +1 484 821 1272

E-mail: sales-us@mn-net.com